



TECHNICAL DATA SHEET PITTURA LAVABILE AL QUARZO (QUARTZBASED WASHABLE PIAINT)

CREATION DATE 06/03/2020
Rev. 0

GENERAL INFORMATIONS		
Special effect washable waterborne wallpaint. Its characteristics are set, ideally, between a plastic coating and a washable exterior paint. The final aspect is an embossed-like film but without a classical "orange peel" effect. It is alkalines resistant and this paint can be applied on every kind of plaster (previously treated)		
CHEMICAL AND PHISYCAL CHARACTERISTICS		
		NOTES
SPECIFIC GRAVITY	1,5 ± 0,1 Kg/L	
VISCOSITY	Thixotropic	Brookfield method
SOLID CONTENT	70 ± 1% (by weight)	Theoretical calculation
SPREAD REATING: (2 coats)	400 g/m ²	Theoretical calculation
CATALYSIS	This product does not require catalysis	
BINDER NATURE	Vinyl copolymer	
APPLICATIONS CHARACTERISTICS		
APPLICATION MODE		
BRUSH, ROLL	Dil. 25% with DEMINERALIZED WATER	
DRYING TIMES	It dries between 3-9 hours according to environmental conditions. Minimum drying temperature is 5°C	
<i>Hardening times can change considerably according to temperature and thickness of the application.</i>		
OVERPAINTING		
This product is over paintable after 12-24 hours		
SURAFACES TREATMENT		
The surfaces must be free from impurity and previous coatings residues		
ENVIRONMENTAL CONDITIONS		
Minimum drying temperature is 5°C		
TOOLS CLEANINGS		
Tools can be easily cleaned from impurities by using WATER.		
STOCK		
This product is stable for 12 months if it is conserved in sealed buckets.		

The information given in this sheet and founded on our experience are not intended to be fully exhaustive. Whilst we endeavour to ensure that all advices we give about the product (whether in this sheet or otherwise) are correct, we have no control over either the quality or condition of the substrate or the many factors affecting the use and application of the product. Is supposed that every user liberally opts for the products described on this sheet, after verifying suitability according its requirements. This product is intended for use only by professional applicators in industrial, according the advices described on this sheet, the material safety data sheet and the packaging