

TECHNICAL DATA SHEET

TRASPIRANTE SUPERCOPRENTE

(SUPEROPACITY TRANSPIRANT WALLPAINT)

Doc. creation date 04/06/2020
Rev. 0

GENERAL INFORMATIONS		
Interior wall paint. It has good opacity, white point, viscosity and brush applications distension properties.		
CHEMICAL AND PHYSICAL CHARACTERISTICS		
		NOTE
SPECIFIC GRAVITY	1.6 ± 0,1 Kg/L	
VISCOSITY	Thixotropic	
SOLID CONTENT	66 ± 1% (by weight)	Theoretical calculation
SPREAD REATING: (dry 50 µm)	9-7 m ² /L	Theoretical calculation
CATALYSIS	This product does not require catalysis	
BINDER NATURE	Acrylic copolymers	

APPLICATIONS CHARACTERISTICS	
APPLICATION MODE	
BRUSH, ROLLER	First coat dil. 30-40% with DEMINERALIZED WATER. Second coat dil. 20-25% con DEMINERALIZED WATER
NEW WALLS	TRASPIRANTE SUPERCOPRENTE applies in two coat on civil plaster and chalky plaster, after a properly treatment with vinyl or acrylic fixative
OLD WALLS	Brush the wall, eventually grout it and that treat it with an acrylic or vinyl fixative product. After that, apply two coat of TRASPIRANTE SUPERCOPRENTE.
<i>Hardening times can change considerably according to temperature and thickness of the application.</i>	

SURFACES TREATMENT
This product are over paintable with itself after 12-24 hours
ENVIRONMENTAL CONDITIONS
External temperature and temperature of surfaces must be 3 degrees above the dew point
TOOLS CLEANINGS
Tools can be easily cleaned from impurities by using WATER.
STORAGE
TRASPIRANTE SUPERCOPRENTE is stable for 12 months if it is conserved in sealed buckets.



TECHNICAL DATA SHEET
TRASPIRANTE SUPERCOPRENTE
(SUPEROPACITY TRANSPIRANT WALLPAINT)

Doc. creation date 04/06/2020
Rev. 0

The information given in this sheet and founded on our experience are not intended to be fully exhaustive. Whilst we endeavour to ensure that all advices we give about the product (whether in this sheet or otherwise) are correct, we have no control over either the quality or condition of the substrate or the many factors affecting the use and application of the product. Is supposed that every user liberally opts for the products described on this sheet, after verifying suitability according its requirements. This product is intended for use only by professional applicators in industrial, according the advices described on this sheet, the material safety data sheet and the packaging