



TECHNICAL DATA SHEET

4LG4.B0099

HOLZ FONDO BIANCO NC 425

(HOLZ PRIMER NC 425 WHITE)

Creation date 16/09/15

Rev. 0

GENERAL INFORMATIONS		
Nitro-alkyd one component primer. It protect wood forming a layer easily sandable. It has a higher spread rate because of it pigmentation		
PHYSICAL AND CHEMICAL CHARACTERISTICS		
		NOTE
SPECIFIC GRAVITY	1,23 ± 0,1 Kg/lt	
VISCOSITY	R4 1000 cP at 20°C	Brookfield method
SOLID CONTENT	55 ± 1% (weight)	Theoretical
BRIGHTNESS	4-5 Gloss	Glossmeter 60°
SPREAD RATE (50 µm DRY)	5 m ² / Kg	Theoretical
AVAILABLE DYES	White	
CATALYSIS	This product does not require catalysis	
BINDER NATURE	Nitro alkyds resins	

TECHNOLOGICAL CHARCTERISTICS	
APPLICATION MODES	
BRUSH, ROLLER	Dil. 5-10% with NITRO THINNER
SPRAY	Dil 15-20% NITRO THINNER. Pressure: 3 bar Nozzle diameter: 1.5 mm
EXSICCATION	
DUST FREE	15 min
TOUCH FREE	40 min
DEEP EXSICCATION	8 ore
<i>Hardening times can change considerably according to temperature and thickness of the application.</i>	

OVERPAINTING
HOLZ PRIMER NC 425 is repaintable after 24 with our HOLZ TOPCOATS
SURFACES PREPARATIONS
Wood must be dry and sanded. Remove all residual by previous coatings and other impurities.
ENVIRONMENTAL CONDITIONS
The temperature of the surface must be above 3 degrees from dew forming temperature
TOOLS CLEANING
NITRO THINNER is suitable for clean dirty tools by not polymerized product.
STOCKING
This product conserve it properties in fresh and dry environments. In a well closed can, PRIMER NC 499 lasts 12 months at least.

Vivcolor s.r.l.



TECHNICAL DATA SHEET

4LG4.B0099

HOLZ FONDO BIANCO NC 425

(HOLZ PRIMER NC 425 WHITE)

Creation date 16/09/15

Rev. 0

The information given in this sheet and founded on our experience are not intended to be fully exhaustive. Whilst we endeavour to ensure that all advices we give about the product (whether in this sheet or otherwise) are correct, we have no control over either the quality or condition of the substrate or the many factors affecting the use and application of the product. It is supposed that every user liberally opts for the products described on this sheet, after verifying suitability according its requirements. This product is intended for use only by professional applicators in industrial, according the advices described on this sheet, the material safety data sheet and the packaging.