



## TECHNICAL DATA SHEET

9FG1W

IDROPRINT

Creation date 28/09/18  
Rev. 1

<b>GENERAL INFORMATION</b>		
Water based protective impregnating paint. IDROPRINT is characterized by high wood wetting properties that enhance aesthetic of wood without stains.		
<b>CHEMICAL AND PHYSICAL CHARACTERISTICS</b>		
		NOTE
SPECIFIC GRAVITY	1,05 ± 0,05 Kg/lt	
VISCOSITY	R2 200cP at T. 20°C	
SOLID CONTENT	23 ± 2% (by weight)	theoretical
SPREAD RATE: (50 µm dry)	-- m <sup>2</sup> /Kg	Not available
VOC g/L (DIR. 2010/75/CE)	20,00 gr/l	This value is referred to DECORVIV TRANSPARENT. Please see SDS for dyes value
AVAILABLE DYES	RAL palette, DECORVIV palette, on request	
CATALYSIS	This product does not requires catalysis	
BINDER NATURE	Alkyd resins	

<b>APPLICATION MODE</b>	
ROLLER, BRUSH	Ready to use product.
SPRAY	Ready to use product.
<i>EXSICCATION</i>	
DUST FREE	30 minutes
TOUCH FREE	1 hours
DEEP ESSICATION	8 hours
COMPLETE ESSICATION	12 hours

<b>OVERPAINTING</b>
IDROPRINT can be repainted by spray, roll or brush applications in two coats intersperse by 4-6 hours
<b>SURFACES PREPARATIONS</b>
Wood must be dust free and dried. New woods, in order to obtain better final effect, can be sanded. Old wood, instead, must be free from impurities and old applications residuals
<b>ENVIRONMENTAL CONDITIONS</b>
Suggested temperature for applications is between 10° and 30°C and relative humidity under 75%
<b>TOOLS CLEANING</b>
WATER IS suggested for cleaning tools by not polymerized paint
<b>STORAGE</b>
In fresh and dry places. IDROPRINT assure stability for 12 months in well-close can.

# Vivcolor s.r.l.



## TECHNICAL DATA SHEET

9FG1W

IDROPRINT

Creation date 28/09/18

Rev. 1

The information given in this sheet and founded on our experience are not intended to be fully exhaustive. Whilst we endeavour to ensure that all advices we give about the product (whether in this sheet or otherwise) are correct, we have no control over either the quality or condition of the substrate or the many factors affecting the use and application of the product. It is supposed that every user liberally opts for the products described on this sheet, after verifying suitability according its requirements. This product is intended for use only by professional applicators in industrial, according the advices described on this sheet, the material safety data sheet and the packaging.