Vivcolor s.r.l.

TECHNICAL DATA SHEET 8AG4.N0006 SMALTO SILICONICO ALTE T.



Creation date 16/06/15 Rev. 3

GENERAL INFORMATIONS

One-component silicone paint with excellent resistance to high temperatures. It is suitable for the painting of products subjected to continuous temperatures of 500°C and maximum peaks of 600°C such as: fireplaces, interior of ovens not used for food, boilers, mufflers, etc..

etc		
FINISHED PRODUCT CHARACTERISTICS		
		NOTES
SPECIFIC WEIGHT	1.25 ± 0,1 Kg/L	
VISCOSITY	R3 200 cP at 20°C	Brookfield Method
SOLID CONTENT	42 ± 1% (weight)	Theoretical
		calculation
SPREAD RATING: (50 μm secchi)	$8-9 \text{ m}^2/\text{Kg}$	Theoretical
		calculation
OPACITY	3 Gloss	Glossmeter 60°
VOC gr/l (Dir. 2010/75/CE)	369.95 g/L	
AVAIABLE DYIES	Black	
CATALYSIS	This product does not require catalysis	
BINDER NATURE	Silicone and acrylic resin	

TECHNOLOGICAL CHARACTERISTICS AND RESISTANCE TESTS		
APPLICATION MODE		
SPRAY	Dilution 10-15% DILUENTE NITRO ANTINEBBIA or DILUENTE SINTETICO. Nozzle pressure: 3 bar Nozzle diameter: 1.7 mm	
The product must be applied microns.	in thicknesses not exceeding 20-25 dry	
HARDENING		
DUST FREE	15 min	
TOUCH FREE	1 hour	
DEEP HARDENING	24 hours	
COMPLETE DRYING	After cooking, 10/20' at 250 °C	
Curing times may vary considerably depending on the thickness applied.		
Temperature can also have a significant influence on the temperature,		
especially on the evaporation of solvents.		

OVERPAINTING

The product is not suitable for overpainting once applied.

SURFACES PREPARATION

The product is applied directly on the metal substrate or on refractory substrates, after verification of adhesion, free of contaminating surfactants.

If anticorrosive properties are required, it is possible to apply our INORGANIC ZINCANTE, 7NG4.ZINCA. In this case, the heat resistance will

Vivcolor s.r.l.

TECHNICAL DATA SHEET 8AG4.N0006 SMALTO SILICONICO ALTE T.



Creation date 16/06/15 Rev. 3

decrease up to a temperature of 400 °C.

ENVIRONMENTAL CONDITION

The temperature of the substrate and exterior must be at least 3 degrees above dew point.

TOOLS CLEANING

The tools can be cleaned from the uncured product with DILUENTE NITRO ANTINEBBIA.

STORAGE

In a cool and dry place, and in a well sealed tin, the product is stable for at least 12 months.

The information given in this technical data sheet is indicative and based on our knowledge derived from experience and experimentation and can in no way constitute a guarantee. The purchaser/user decides independently on the suitability of the product for his own requirements in the context of the specific field of use. For safety information please refer to the relevant toxicological data sheet.