

TECHNICAL DATA SHEET

9NG2W00001

VERNICE PELABILE WB TRASPARENTE

Creation date 13/02/18
Rev. 0

GENERAL CHARACTERISTICS		
<p>Removable tear-off paint for the temporary coating of machines and manufactured articles in general (glass, chrome-plated areas, non-porous metal surfaces) to be preserved during periods of inactivity or during shipping, especially during long sea voyages on deck.</p> <p>This product must be applied exclusively on inert, non-porous surfaces that are unalterable from contact with aggressive solvents: all surfaces that do not meet these requirements (e.g. rubber gaskets, painted parts or porous substrates) must be protected in other ways.</p> <p>When the product to which the removable tear-off paint has been applied must be used, the coating can be easily removed in a way similar to an orange peel. The film is generally also removable when repainted with various types of water-based and solvent-based paints*.</p> <p>*It is advisable to check compatibility with the cycle used.</p>		
CHARACTERISTICS OF THE SUPPLY PRODUCT		
		NOTES
SPECIFIC WEIGHT	0.95 ± 0,1 Kg/lt	
VISCOSITY	R4 6500 cP at T. 20°C	
SOLIDS CONTENT	40 ± 1% (weight)	Theoretical
YIELD: (50 µm dry)	Theoretical: 6 m ² /Kg	
VOC gr/l (Dir. 2004/42/CE)	33.82 gr/l	
AVAILABLE COLOURS	All dyes available	
CATALYSIS RATIO	The product does not need specific catalysts.	
NATURE OF THE PRODUCT	Water-based acrylic resin	

TECHNOLOGICAL FEATURES	
APPLICATION MODE	
BRUSH, ROLLER	Dil. 5-10% with demineralised water
SPRAY	Dilution 5 - 10 % with demineralised water.
HARDENING	
DEEP HARDENING	24 hours
COMPLETE DRYING	7 days
<p>Curing times may vary considerably depending on the thickness applied. The temperature can also have a significant influence on the temperature, especially on the evaporation of solvents. The temperature of the substrate must be at least 3 degrees above the dew point.</p>	



TECHNICAL DATA SHEET

9NG2W00001

VERNICE PELABILE WB TRASPARENTE

Creation date 13/02/18
Rev. 0

SURFACES PREPARATION
Surfaces must be thoroughly degreased and free of impurities.
ENVIRONMENTAL CONDITIONS
The temperature of the substrate and exterior must be at least 3 degrees above dew point.
TOOLS CLEANINGS
Tools can be cleaned from the product with water.
STORAGE
In a cool and dry place, and in a well sealed tin, the product is stable for at least 3 months.

The information given in this technical data sheet is indicative and based on our knowledge derived from experience and experimentation and can in no way constitute a guarantee. The purchaser/user decides independently on the suitability of the product for his own requirements in the context of the specific field of use. For safety information please refer to the relevant toxicological data sheet.