

TECHNICAL DATA SHEET VIVFIX

Creation date 18/03/2021
Rev. 0

GENERAL INFORMATION		
Transparent water-based vinyl fixative. Its high substrate impregnation power helps to considerably extend the life of the paintwork.		
TECHNICAL INFORMATIONS		
		NOTE
SPECIFIC WEIGHT	1,6 ± 0,1 Kg/L	
VISCOSITY	1000-1500 cP	Brookfield method
SOLID CONTENT	50 ± 1% (by weight)	Theoretical
YIELD	16-20 m ² /L	Theoretical
CATALISYS	Not required	
AVAILABLE DYES	Transparent	
BINDER NATURE	Vinilic copolymer	

TECHNOLOGICAL INFORMATIONS	
APPLICATIONS MODALITY	
BRUSH, ROLLER	Dil. 600-800% with DEMINERALIZED WATER
SPRAY	Dil. 600-800% with DEMINERALIZED WATER
<i>For spray applications this product have to be filtered</i>	
NEW WALLS	Fill possible imperfections and sandpaper. Then proceed with the application of a coat of product.
OLD WALLS	On already treated plasterwork, remove any detaching coatings. Fill imperfections and sand the substrate. Then proceed with the application of a coat of product.

DRYING	
DUST FREE	n/a
TOUCH FREE	1 hours
DEEP DRYING	4-6 hours
Drying times can vary significantly depending on the thickness applied. A high thickness can compromise the drying in depth. Temperature can also have a significant effect on drying, especially on solvent evaporation. The substrate temperature must be at least 3 degrees above dew point.	

TECHNICAL DATA SHEET VIVFIX

Creation date 18/03/2021
Rev. 0

OVERCOATING
The product can be overpainted after 4-6 hours
ENVIRONMENTAL CONDITION
The substrate and outdoor temperature must be at least 3 degrees above the dew point.
TOOLS CLEANING
Tools can be cleaned of undried product with DEMINERALISED WATER.
STORAGE
In a cool and dry place, and in well sealed tin, the product is stable for at least 12 months. Storage temperature should be between 5°C and 35°C

The information given in this data sheet is indicative and based on our knowledge derived from experience and testing and can in no way constitute a guarantee. The purchaser/user is responsible for determining the suitability of the product for his or her own requirements in the context of the specific field of application. Please refer to the relevant toxicological data sheet for safety information.