

TECHNICAL DATA SHEET VIVWASH

Creation date 14/03/2021
Rev. 0

GENERAL INFORMATION		
Breathable washable paint for interiors with excellent adhesion to the support and good opacity. Thanks to its formulation, this paint prevents the phenomenon of flaking		
TECHNICAL INFORMATIONS		
		NOTE
SPECIFIC WEIGHT	1,55 ± 0,1 Kg/L	
VISCOSITY	13000-18000 cP	Brookfield method
SOLID CONTENT	60 ± 1% (by weight)	Theoretical
YIELD (50 dry µm)	10-12 m ² /L	Theoretical
CATALISYS	Not required	
AVAILABLE DYES	White	
BINDER NATURE	Vinilic copolymer	

TECHNOLOGICAL INFORMATIONS	
APPLICATIONS MODALITY	
BRUSH, ROLLER	Dil. 25-35% with DEMINERALIZED WATER
SPRAY	Dil. 50-60% with DEMINERALIZED WATER
<i>For spray applications this product have to be filtered</i>	
PAINTED WALLS	Brush off any residues of previous processes, dust and impurities. On absorbent supports, use a coat of VIVFIX beforehand. Proceed with the application of 2 or more coats of water-based paint, respecting application times, keeping the first coat of paint slightly (5%) thinner

DRYING	
DUST FREE	n/a
TOUCH FREE	30 min
DEEP DRYING	24 hours
Drying times can vary significantly depending on the thickness applied. A high thickness can compromise the drying in depth. Temperature can also have a significant effect on drying, especially on solvent evaporation. The substrate temperature must be at least 3 degrees above dew point.	

TECHNICAL DATA SHEET VIVWASH

Creation date 14/03/2021
Rev. 0

OVERCOATING
The product can be overpainted after 4-6 hours
ENVIRONMENTAL CONDITION
The substrate and outdoor temperature must be at least 3 degrees above the dew point.
TOOLS CLEANING
Tools can be cleaned of undried product with DEMINERALISED WATER.
STORAGE
In a cool and dry place, and in well sealed tin, the product is stable for at least 12 months. Storage temperature should be between 5°C and 35°C

The information given in this data sheet is indicative and based on our knowledge derived from experience and testing and can in no way constitute a guarantee. The purchaser/user is responsible for determining the suitability of the product for his or her own requirements in the context of the specific field of application. Please refer to the relevant toxicological data sheet for safety information.