Vivcolor s.r.l.

TECHNICAL DATA SHEET JBG4 SILICONIC PRIMER 250°C





Creation date Rev.

31/08/21

GENERAL INFORMATION

Primer based on high-quality silicone and acrylic resins and anticorrosion agents, suitable for painting iron or steel structures that can reach temperatures of 250°C and require anti-corrosion protection.

FINISHED PRODUCT CHARACTERISTIC			
SPECIFIC WEIGHT	$1.06 \pm 0,1 \text{ Kg/L}$		
VISCOSITY	R3 300 cP at 20°C	Brookfield method	
SOLID CONTENT	42 ± 1% (weight)	Theoretical	
YIELD: (50 dry μm)	8-9 m²/Kg	Theoretical	
BRIGHTNESS	4-5 Gloss	Pre-baking	
	1 Gloss	After baking	
AVAIABLE DYES	Black, Red, Green, Blue, Purple, Aluminium. All pastel colours are also available with metallic effect.		
CATALYSIS	This product does not	This product does not require catalysis	
BINDER NATURE	Silicone and acrylic resin		

TECHNOLOGICAL CHARACTERISTICS AND RESISTANCE TESTS		
APPLICATION MODE		
SPRAY	Dilution 0-10% SYNTHETIC DILUENT.	
	Nozzle pressure: 3 bar	
	Nozzle diameter: 1.2 mm	
RECOMMENDED THICKNESSES	30 dry μm (100 wet μm)	
HARDENING		
DUST FREE	15 min	
TOUCH FREE	1 hour	
DEEP HARDENING	12-24 hours	
The product physically dries at room temperature, the final hardening		
takes place when the temperature of 200°C or higher is reached.		

OVERPAINTING

The product is not suitable for overpainting once applied.

SURFACES PREPARATION

Surfaces must be thoroughly degreased and free of impurities.

ENVIRONMENTAL CONDITIONS

The temperature of the substrate and exterior must be at least 3 degrees above dew point.

TOOLS CLEANINGS

The tools can be cleaned from the uncured product with NITRO THINNER

Vivcolor s.r.l.

TECHNICAL DATA SHEET JBG4 SILICONIC PRIMER 250°C





Creation date Rev.

31/08/21

STORAGE

In a cool and dry place, and in a well sealed tin, the product is stable for at least 12 months.

The information given in this technical data sheet is indicative and based on our knowledge derived from experience and experimentation and can in no way constitute a guarantee. The purchaser/user decides independently on the suitability of the product for his own requirements in the context of the specific field of use. For safety information please refer to the relevant toxicological data sheet.