

## TECHNICAL DATA SHEET SILOXVIV

Data creazione 18/03/21  
Data aggiorn. 24/04/25  
Rev. 1

| GENERAL INFORMATION  |                             |             |
|--|-----------------------------|-------------|
| Quartz water paint based on acrylic-siloxane resins, with an organo-mineral matrix. It guarantees high breathability, water repellency and protection from driving rain, while keeping the substrate dry. Versatile, low dirt pick-up and additivated with phase-release coated biocides for prolonged protection against algae and mould. |                             |             |
| TECHNICAL INFORMATIONS   |                             |             |
|  |                             | NOTE        |
| YIELD (50 dry $\mu\text{m}$ )  | 8-10 $\text{m}^2/\text{L}$  | Theoretical |
| AVAILABLE DYES   | White or colours on request |             |

| TECHNOLOGICAL INFORMATIONS |   |
|----------------------------|---|
| APPLICATIONS MODALITY      |   |
| BRUSH, ROLLER              | Dil. 30-40% with DEMINERALIZED WATER  |
| NEW WALLS                  | Brush off any dust and impurities. On absorbent supports, use a coat of <b>VIVFIX</b> beforehand. Proceed with the application of 2 or more coats of water-based paint, respecting the application times.                     |
| OLD WALLS                  | Remove any paint that is detaching, then fill and sand. On absorbent supports, use a coat of <b>VIVFIX</b> beforehand. Proceed with the application of 2 or more coats of water-based paint, respecting the application times |

| DRYING  |          |
|---|----------|
| DUST FREE   | n/a      |
| TOUCH FREE  | 1 hours  |
| DEEP DRYING   | 24 hours |
| Drying times can vary significantly depending on the thickness applied. |          |

## TECHNICAL DATA SHEET SILOXVIV

Data creazione 18/03/21  
Data aggiorn. 24/04/25  
Rev. 1

|   |
|---|
| <b>OVERCOATING</b>  |
| The product can be overpainted after 4 hours  |
| <b>ENVIRONMENTAL CONDITION</b>  |
| The substrate and outdoor temperature must be at least 3 degrees above the dew point.   |
| <b>TOOLS CLEANING</b>   |
| Tools can be cleaned of undried product with DEMINERALISED WATER.   |
| <b>STORAGE</b>  |
| In a cool and dry place, and in well sealed tin, the product is stable for at least 12 months. Storage temperature should be between 5°C and 35°C |

The information given in this data sheet is indicative and based on our knowledge derived from experience and testing and can in no way constitute a guarantee. The purchaser/user is responsible for determining the suitability of the product for his or her own requirements in the context of the specific field of application. Please refer to the relevant toxicological data sheet for safety information.