

## TECHNICAL DATA SHEET VIVAIR ANTIMUFFA

Creation date 22/04/25  
Rev. 0

| GENERAL INFORMATION  |                                    |             |
|--|------------------------------------|-------------|
| Antimould wall paint with excellent whiteness, high breathability, good masking power and easy application. It is ideal for quality interior finishes, contains anti-fungal active ingredients and complies with UNI EN 15457. Low emission. |                                    |             |
| TECHNICAL INFORMATIONS   |                                    |             |
|  |                                    | NOTE        |
| YIELD (50 dry $\mu\text{m}$ )  | 9-11 $\text{m}^2/\text{L}$ by hand | Theoretical |
| AVAILABLE DYES   | White                              |             |

| TECHNOLOGICAL INFORMATIONS |   |
|----------------------------|---|
| APPLICATIONS MODALITY      |   |
| BRUSH, ROLLER              | Dil. 30-40% with DEMINERALIZED WATER  |
| NEW WALLS                  | Brush off any dust and impurities. On supports with high absorption power, use a coat of VIVFIX beforehand. Proceed with the application of 2 or more coats of water-based paint, respecting application times.       |
| OLD WALLS                  | Remove any paint that is detaching, then fill and sand. On supports with high absorption power, use a coat of VIVFIX beforehand. Proceed with the application, keeping the first coat of paint slightly (5%) thinner. |

| DRYING  |          |
|---|----------|
| DUST FREE   | n/a      |
| TOUCH FREE  | 30 min   |
| DEEP DRYING   | 24 hours |
| Drying times can vary significantly depending on the thickness applied. |          |

## TECHNICAL DATA SHEET VIVAIR ANTIMUFFA

Creation date 22/04/25  
Rev. 0

|   |
|---|
| <b>OVERCOATING</b>  |
| The product can be overpainted after 4 hours  |
| <b>ENVIRONMENTAL CONDITION</b>  |
| The substrate and outdoor temperature must be at least 3 degrees above the dew point.   |
| <b>TOOLS CLEANING</b>   |
| Tools can be cleaned of undried product with DEMINERALISED WATER.   |
| <b>STORAGE</b>  |
| In a cool and dry place, and in well sealed tin, the product is stable for at least 12 months. Storage temperature should be between 5°C and 35°C |

The information given in this data sheet is indicative and based on our knowledge derived from experience and testing and can in no way constitute a guarantee. The purchaser/user is responsible for determining the suitability of the product for his or her own requirements in the context of the specific field of application. Please refer to the relevant toxicological data sheet for safety information.