

## TECHNICAL DATA SHEET VIVQUARTZ

Creation date 14/03/21  
Latest update 22/04/25  
Rev. 1

GENERAL INFORMATION		
Professional quartz paint based on styrene-acrylic resins, with very high yield, excellent coverage and resistance to washing. It forms a thin, weatherproof and pollutant-resistant film, ideal for new or old substrates, guaranteeing long-lasting work. Additivated with time-release coated biocides, it offers prolonged protection against algae and mould.		
TECHNICAL INFORMATIONS		
		NOTE
YIELD (75 dry $\mu\text{m}$ )	8-10 $\text{m}^2/\text{L}$	Theoretical
AVAILABLE DYES	White and white-derived dyes	

TECHNOLOGICAL INFORMATIONS	
APPLICATIONS MODALITY	
BRUSH, ROLLER	Dil. 25-35% with DEMINERALIZED WATER
NEW WALLS	Brush off any dust and impurities. On absorbent supports, use a coat of <b>VIVFIX</b> beforehand. Proceed with the application of 2 or more coats of water-based paint, respecting the application times.
OLD WALLS	Remove any detaching paint, then fill and sand. Proceed with the application, keeping the first coat of paint slightly thinned (5%)

DRYING	
DUST FREE	n/a
TOUCH FREE	1 hours
DEEP DRYING	24 hours
Drying times can vary significantly depending on the thickness applied.	

## TECHNICAL DATA SHEET VIVQUARTZ

Creation date 14/03/21  
Latest update 22/04/25  
Rev. 1

<b>OVERCOATING</b>
The product can be overpainted after 4-6 hours
<b>ENVIRONMENTAL CONDITION</b>
The substrate and outdoor temperature must be at least 3 degrees above the dew point.
<b>TOOLS CLEANING</b>
Tools can be cleaned of undried product with DEMINERALISED WATER.
<b>STORAGE</b>
In a cool and dry place, and in well sealed tin, the product is stable for at least 12 months. Storage temperature should be between 5°C and 35°C

The information given in this data sheet is indicative and based on our knowledge derived from experience and testing and can in no way constitute a guarantee. The purchaser/user is responsible for determining the suitability of the product for his or her own requirements in the context of the specific field of application. Please refer to the relevant toxicological data sheet for safety information.