

TECHNICAL DATA SHEET

2AG4I

ACRIVIV 70.100 MATT S.I. (SPECIAL INOX)

Creation date 19/02/21
Latest update 26/05/25
Rev. 0

GENERAL CHARACTERISTICS		
Single-coat matt two-component enamel with high weather resistance, good passivating power, maximum resistance to aggressive chemicals (detergents etc.), very low flammability, good elasticity, excellent gloss retention and high coverage. The enamel is particularly suitable for industrial use for the direct painting of metal substrates such as iron, light alloys, galvanised iron and stainless steel without the need for any primer or abrasive surface treatment. The applied film is matt with high surface hardness.		
CHARACTERISTIC OF THE SUPPLY PRODUCT		
		NOTES
SPECIFIC WEIGHT	1.2 ± 0,1 Kg/L 1.15 ± 0.1 Kg/L (A+B)	
VISCOSITY	R4 5000 cP 20°C	
SOLID CONTENT	70 ± 2% (weight) 55 ± 2% (volume)	Theoretical
SPREAD RATIO (50 µm dry)	8,5 m²/Kg	Theoretical
BRIGHTNESS	10-15 GLOSS	Glossmeter 60°
CATALYSIS RATIO	WEIGHT: 100 (2AG2) + 10 (HDR2.001) VOLUME: 100 (2AG2) + 15 (HDR2.001)	
PRODUCT NATURE	Hydroxylated acrylic resin.	

TECHNOLOGICAL CHARACTERISTICS AND RESISTANCE TESTS	
RESISTANCE	
ATMOSPHERIC AGENTS	Excellent
NORMAL INDUSTRIAL ATMOSPHERE	Very good
HEAVY INDUSTRIAL ATMOSPHERE	Very good
MARINE ATMOSPHERE	Good
HIGH HUMIDITY ENVIRONMENTS	Excellent
ALCOHOLS	Good
OILS AND FATS	Very good
AROMATIC SOLVENTS	Good
ALIPHATIC SOLVENTS	Very good
TEMPERATURE	When this enamel is applied (completely dried and with a film free of imperfections), it has a continuous heat resistance of approx. 90-100°C. Above this temperature, the technical characteristics of the product are not guaranteed.



TECHNICAL DATA SHEET

2AG4I

ACRIVIV 70.100 MATT S.I. (SPECIAL INOX)

Creation date 19/02/21
Latest update 26/05/25
Rev. 0

APPLICATION MODE	
SPRAY	Dilution 10-20% TH2.1696 ACRYLIC THINNER Nozzle pressure: 3-4 atm Nozzle diameter: 1.8 mm
POT LIFE	4 Hours (high temperatures can also significantly reduce the operating time).

HARDENING	
OUT DUST	40 min
OUT OF TACT	2-4 hours
IN-DEPTH	8-10 hours
COMPLETE HARDENING	7-10 days
<i>Hardening can also be done in the oven at 80°C max (40'), after a flash off time of 20 minutes.</i>	

OVERPAINTING
The product is suitable for overpainting once applied. In the following 24 hours after application it is advisable to sand finely.
SURFACES PREPARATION
Degrease thoroughly in accordance with norm. SSPC-SP1. Ferrous surfaces with calamine and/or rust must be treated by commercial sandblasting SIS Sa2. Fresh galvanised surfaces, before painting, must be treated by washing with degreasing agents or acids in order to achieve thorough cleaning of the substrate. For maximum adhesion, apply the paint in a very thin layer (40-60 microns or the amount needed to achieve coverage). For stainless steel (INOX) surfaces, traces of grease and any impurities on the surface must be removed, if present.
ENVIRONMENTAL CONDITIONS
Particularly cold temperatures or environments with high relative humidity can slow down or change the characteristics of the system, which is affected during the painting phase by atmospheric conditions. It is therefore recommended to apply and initial drying in environments with a temperature above 10-15 °C and a maximum relative humidity of 75%. Light rain, high humidity or condensation during the 16 hours following application (20°C) can irreversibly corrupt the film formation. At temperatures above 25-30°C it is advisable to use a special retardant thinner or more of the thinner usually used, in order to avoid the formation of dots and bubbles (pin points) on the paint film.



TECHNICAL DATA SHEET

2AG4I

ACRIVIV 70.100 MATT S.I. (SPECIAL INOX)

Creation date	19/02/21
Latest update	26/05/25
Rev.	0

TOOLS CLEANING

The tools can be cleaned from the uncured product with NITRO thinner.

STORAGE

In a cool and dry place, protected from direct sunlight and in a well sealed tin, ACRIVIV is stable for at least 12 months, the HARDENER at least 6 months. Particular attention must be paid to the storage of the HARDENER which, being susceptible to react with atmospheric humidity, once opened it must be consumed as soon as possible and at the same time stored in particularly dry environments.

The information given in this technical data sheet is indicative and based on our knowledge derived from experience and experimentation and can in no way constitute a guarantee. The purchaser/user decides independently on the suitability of the product for his own requirements in the context of the specific field of use. For safety information please refer to the relevant toxicological data sheet.