

## TECHNICAL DATA SHEET

2AG1P

ACRIVIV 70.00 GLOSSY FLOORING

Creation date 11/07/25  
Rev. 0

GENERAL INFORMATIONS		
A two-component, glossy acrylic finish with high weather and scratch resistance and good resistance to aggressive chemicals. This particular enamel is suitable for applications on concrete and floors. The textured version has excellent anti-slip properties.		
PHISICAL AND CHEMICAL CHARACTERISTICS		
		NOTE
SPECIFIC WEIGHT	1,15 ± 0,1 Kg/L (A)	
VISCOSITY	R3 900 cP a 20°C	Brookfield Method
SOLID CONTENT	57 ± 1% (by weight) A+B	Theoretical
YIELD: (100 µm dry)	5,5 m <sup>2</sup> /Kg	Theoretical
BRIGHTNESS	100 Gloss	Glossmeter 60°
AVAIALE DYES	RAL, Pantone, NCS and on request	
CATALYSIS	25% with HDR2.001 (by weight) 27% with HDR2.001 (by volume)	
BINDER NATURE	Hydroxilated acrylic resins	

TECHNOLOGICAL AND RESISTANCES CHARACTERISTICS	
RESISTANCES	
ATMOSPHERIC AGENTS	Excellent
NORMAL INDUSTRIAL ENVIROMENTS	Really Good
HEAVY INDUSTRIAL ENVIROMENTS	Really Good
SEA ENVIROMENTS	Good
HIGH UMIDITY ENVIROMENTS	Excellent
ALCOHOLS	Good
FATS AND OILS	Really Good
AROMATIC SOLVENTS	Good
ALIFATIC SOLVENTS	Really Good
TEMPERATURE	Max: 90-100°C (at complete hardening)

APPLICATION	
BRUSH OR ROLLER	Dil. 0-5% TH2.002 (SLOW ACRYLIC THINNER)
SPRAY	Dil. 5-10% TH2.1696 (ACRYLIC THINNER). Pressure: 3-4 bar Ø nozzle: 1.8 mm Suggested thickness (on dry film): 40-50 µm
POT LIFE	3 hours (high temperature can reduce significantly pot life times)



## TECHNICAL DATA SHEET

2AG1P

ACRIVIV 70.00 GLOSSY FLOORING

Creation date  
Rev.

11/07/25  
0

HARDENING TIMES	
DUST FREE	40 mins
TOUCH FREE	2-4 mins
DEEP HARDENING	8-10 hours
COMPLETE HARDENING	7 days
<i>Hardening times can change significantly according to temperature and thickness of the application.</i>	

<b>OVERPAINTING</b>
The product is suitable for overpainting once applied. Within 24 hours after application, it is advisable to sand finely.
<b>SURFACES PREPARATIONS</b>
<p>Remove loose parts: Remove any loose parts from the surface, such as old peeling paint or debris.</p> <p>Dusting: Thoroughly clean the surface with a brush or cloth to remove dust and debris.</p> <p>Make sure the surface is dry: Do not apply the enamel to damp surfaces or surfaces subject to rising damp. If in doubt, wait for the surface to dry completely.</p> <p>Remove contaminants: For best adhesion, it is essential to remove traces of oils, greases, silicones and old paints. If a completely clean surface cannot be achieved, light sandblasting is recommended.</p> <p>Pre-treatment for helicopter concrete surfaces: For very shiny and smooth surfaces, pre-treatment with muriatic acid (minimum concentration 6%) is necessary. Leave the acid to react completely and rinse thoroughly with tap water. Make sure the surface is completely dry before applying the enamel.</p> <p>Do not apply on damp substrates or those subject to rising damp. Always check the residual moisture content (<math>\leq 3\%</math> by weight) before painting.</p>



## TECHNICAL DATA SHEET

2AG1P

ACRIVIV 70.00 GLOSSY FLOORING

Creation date  
Rev.

11/07/25  
0

### ENVIROMENTAL CONDITIONS

Particularly cold temperatures or environments with high relative humidity can slow down or change the characteristics of the system, which is affected during the painting phase by atmospheric conditions. We therefore recommend application and initial drying in environments with a temperature of more than 10-15°C and a maximum relative humidity of 75 %. Light rain, high humidity or the formation of condensation during the 16 hours following application can irreversibly damage the film formation. At temperatures above 25-30°C it is advisable to use a suitable retardant thinner or a larger amount of the thinner normally used, in order to avoid the formation of dots and bubbles (pinpricks) on the paint film.

### TOOLS CLEANING

Tools can be cleaned, by not polymerized product, with TH4.1000 NITRO THINNER.

### STORAGE

In fresh and low humidity places, avoiding direct contact with sunlight and in a well sealed can, the product is stable for 12 months. His hardener, in the same conditions, is stable 6 months.

The information given in this sheet and founded on our experience are not intended to be fully exhaustive. Whilst we endeavour to ensure that all advices we give about the product (whether in this sheet or otherwise) are correct, we have no control over either the quality or condition of the substrate or the many factors affecting the use and application of the product. Is supposed that every user liberally opts for the products described on this sheet, after verifying suitability according its requirements. This product is intended for use only by professional applicators in industrial, according the advices described on this sheet, the material safety data sheet and the packaging.